

Technical Data Sheet
Hydrosize® PE1-01
Polyethylene Dispersion

Description: Functionalized polyethylene dispersion

Attributes

- Solvent-free, and HAPS free
- Excellent adhesion with fiber reinforced polyethylene composites
- May be used as an antiblocking/release agent

Compatibility

- Polyethylene

Applications

- Fiber reinforcements
- Adhesives
- Coatings
- Textiles

Typical Properties	
Viscosity (cP)	50 - 1000
Non-Volatiles (%)	38 - 42
pH	6.5 – 8.5
Stabilization Mechanism	Anionic / Nonionic
Particle Size (µm)	< 1
Specific Gravity (g/mL)	0.96 – 1.0
Appearance	Translucent Amber Liquid
Flash Point (°C)	N/A

Technical Support: Michelman scientists have extensive knowledge and practical experience with binders and sizings, their application to fibers, and their influence on composite properties. Please do not hesitate to request our assistance. The test methods used to determine the reported properties are available upon request.

Storage: To ensure maximum stability and properties this dispersion should be stored between 5°C (41°F) and 20°C (68°F). PREVENT FREEZING. The product should be stored indoors in tightly closed containers away from heat sources and sunlight. If frozen, warm to room temperature and mix well before using. All storage areas should conform to local fire and building codes. Hydrosize® PE1-01 should be stored away from all sources of flame or combustion.

Standard Package: Non-returnable, plastic or lined fiberwall drums of 450 lbs. net weight.

Safety: Read and understand the Material Safety Data Sheet before working with this product.

Technical Data Sheet
Hydrosize® PE1-01
Polyethylene Dispersion

Michelman, Inc.	9080 Shell Road Cincinnati, Ohio 45236-1299 USA Tel: +1 513 793 7766 Fax: +1 513 793 2504
Michelman SARL	89D Rue Pafebruch, L-8308 Capellen Grand Duché de Luxembourg Tel: +352 26 39 441 Fax: +352 26 39 4480
Michelman Asia-Pacific Pte. Ltd.	2A Tuas Avenue 12 Singapore 639023 Tel: +65 6861 2822 Fax: +65 6861 2262
China Inquiries: Michelman Asia, Inc.	Office 3042, Central Place, No. 16 Henan Road South Shanghai, China 200002 Tel: +86 21 6120 4404 Fax: +86 21 6374 3778

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. For the same reason, the products discussed are sold without warranty, express or implied and on the condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. © 2009 MICHELMAN, INC. All rights reserved.

All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9000 certified.